The Patent Office

PCT/GB 00 / 00323

09/89[illegible]694

INVESTOR IN PEOPLE

4

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

GB00/323

REC'D 06 MAR 2000
WIPO PCT

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.

PRIORITY DOCUMENT

SUBMITTED OR TRANSMITTED IN COMPLIANCE WITH RULE 17.1(a) OR (b)

Signed

Dated 24 February 2000

Patents Form 1/77

... Act 1977
(... 16)

THE PATENT OFFICE
-5 FEB 1999
RECEIVED BY POST

The Patent Office

05FEB99 E422964-5 D02884
P01/7700 0.00 - 9902477.0

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

The Patent Office

Cardiff Road
Newport
Gwent NP9 1RH

1. Your reference: P23140/ALO/CLF/PPP

2. Patent application number *(The Patent Office will fill in this part)*: 9902477.0 — -5 FEB 1999

3. Full name, address and postcode of the or of each applicant *(underline all surnames)*:
The University Court of the University of Glasgow
University Avenue
Glasgow
G12 8QQ

Patents ADP number *(if you know it)*

If the applicant is a corporate body, give the country/state of its incorporation: United Kingdom

4. Title of the invention: "Optical Waveguide with Multiple Core Layers and Method of Fabrication Thereof"

5. Name of your agent *(if you have one)*: Murgitroyd & Company

"Address for service" in the United Kingdom to which all correspondence should be sent *(including the postcode)*:
373 Scotland Street
GLASGOW
G5 8QA

Patents ADP number *(if you know it)*: 1198013

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and *(if you know it)* the or each application number

Country	Priority application number *(if you know it)*	Date of filing *(day / month / year)*

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application	Date of filing *(day / month / year)*

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? *(Answer 'Yes' if:*
a) any applicant named in part 3 is not an inventor, or
b) there is an inventor who is not named as an applicant, or
c) any named applicant is a corporate body.
See note (d))

Yes

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form	–
Description	12
Claim(s)	11
Abstract	1
Drawing(s)	2 +2

10. If you are also filing any of the following, state how many against each item.

Priority documents	–
Translations of priority documents	–
Statement of inventorship and right to grant of a patent *(Patents Form 7/77)*	2
Request for preliminary examination and search *(Patents Form 9/77)*	1
Request for substantive examination *(Patents Form 10/77)*	–
Any other documents *(please specify)*	–

11. I/We request the grant of a patent on the basis of this application.

Signature: Murgitroyd & Company — Date: 4 February 1999

12. Name and daytime telephone number of person to contact in the United Kingdom: Paolo Pacitti — 0141 307 8400

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

a) *If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.*

b) *Write your answers in capital letters using black ink or you may type them.*

c) *If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.*

d) *If you have answered 'Yes' Patents Form 7/77 will need to be filed.*

e) *Once you have filled in the form you must remember to sign and date it.*

f) *For details of the fee and ways to pay please contact the Patent Office.*

OPTICAL WAVEGUIDE WITH MULTIPLE CORE LAYERS AND METHOD OF FABRICATION THEREOF

FIELD OF THE INVENTION

This invention relates to an optical waveguide with multiple core layers and a method of fabrication thereof.

In particular, the invention relates to a doped planar waveguide with multiple core layers and which includes both active and passive components and to a method of fabricating a planar waveguide for an optical circuit in which the core is composed of layers of different materials.

BACKGROUND OF THE INVENTION

Planar waveguides can be passive devices or can include active components; for example, modulators, couplers, and switches. Planar waveguides incorporating active components are extremely advantageous as they can be used to provide integrated optic packages which can serve as complete transmitting modules with, for example, components for amplitude or phase modulation, or multiplexing in an optical

communication network.

Rare earth doped fibre amplifiers, for example erbium or neodymium doped fibre amplifiers, are known to have several advantages in optical communication networks such as high gain, low noise, high power conversion efficiency and wide spectral bandwidth. The present invention seeks to provide the same advantages in planar rare earth doped waveguides and moreover to provide a laser waveguide amplifier which can be used, for example, in an optical communication network to amplify attenuated signals.

Planar waveguide technology is important in the fabrication of lasers and optical amplifiers due to the superior stability, compact geometry of planar waveguide technology. Also, active components, for example modulators, can be integrated into the planar device.

A variety of techniques, including flame hydrolysis deposition (FHD), sputtering, plasma enhanced chemical vapour deposition (CVD) and ion-exchange can be used in the fabrication of silica-based planar waveguides doped with rare-earth ions and which display laser characteristics.

In such laser amplifying waveguides, it is desirable to obtain a high concentration of rare earth ions in order to achieve very compact and efficient devices. However, high concentrations of rare earth ions in a waveguide layer with relatively low solubility can result in the formation of clusters of rare earth ions. The interaction between the rare earth ions in such clusters quenches the excited state required for the lasing process and thus degrades the optical

amplification provided by the waveguide.

Other complications arise in the fabrication of laser waveguides for applications which require single mode transmission, narrow spectral bandwidths, and/or precise control of the lasing wavelength depend critically on their cavity type. Laser waveguides which have butt-coupled mirrors on the waveguide ends or dielectric reflection mirrors are known in the art but suffer to a greater or lesser degree from certain disadvantages; for example, low spectral selectivity.

Bragg gratings incorporated in a waveguide core can provide enhanced spectral selectivity. The fabrication of such gratings is affected by the host glass composition present in the waveguide core which determine the UV absorption band of the core material and thus its photosensitive properties. For example, if phosphorus is used as a core dopant ion it can alleviate the formation of rare earth ion clusters but has the disadvantage that it reduces the amount of absorption in the UV and thus reduces the photosensitivity of the core. If germanium is used as a core dopant ion it can increase the photosensitivity of the core but has the disadvantage of promoting rare earth cluster formation.

The introduction of a Bragg grating can be effected in a planar waveguide by a number of known methods which suffer to a greater or lesser degree from certain disadvantages. The invention provides an optical waveguide with multiple core layers which is suitable for forming a laser waveguide with a high degree of spectral selectivity. The waveguide core combines two different types of silica based layers and these core layers obviate or mitigate the aforementioned

disadvantages which arise when seeking to fabricate an in-core Bragg grating to enhance the spectral selectivity of the laser waveguide. The waveguide formed enables in-core Bragg grating formation at a range of UV wavelengths above 150 nm.

SUMMARY OF THE INVENTION

In accordance with a first aspect of the invention there is provided an optical waveguide with multiple core layers comprising:

In accordance with a second aspect of the invention there is provided a laser waveguide with multiple core layers comprising:

In accordance with a third aspect of the invention there is provided a method of fabricating an optical waveguide with multiple core layers comprising:

In accordance with a fourth aspect of the invention there is provided a method of fabricating a laser waveguide with multiple core layers comprising:

DESCRIPTION OF THE DRAWINGS

Embodiments of the present invention will now be described, by way of example only, with reference to the accompanying drawings, in which:-

Figs. 1A to 1C are schematic cross-sectional diagrams of a waveguide with multiple core layers during various stages of fabrication.

Fig. 2A is a schematic representation of a laser waveguide formed from the waveguide shown in Figs. 1A to 1C; and

Fig. 2B is a detail, to an enlarged scale, of the structure shown in Fig. 2A.

DETAILED DESCRIPTION OF THE INVENTION

Referring now to the drawings, Figs. 1A to 1C illustrate schematically stages in the fabrication of a waveguide with a multi-layered core according to the invention.

Referring now to Fig. 1A, there is illustrated a waveguide 1 which is fabricated from a substrate 2. The substrate 2 comprises a silicon wafer. However, other suitable substrates including silica and sapphire, may be used.

A silica buffer layer 3, comprising a thermally oxidised layer of the substrate 2, is formed on the substrate 2. The thickness of the buffer layer 3 is 15 μm which lies in a preferred range of 5 μm to 20 μm.

A suitable method, for example, a flame hydrolysis deposition (FHD) method, is used to deposit a first core layer 4 on top of the buffer layer 3. The thickness of the first core layer 4 is 2 μm which lies in a preferred range of 0.2 μm to 30 μm.

The material included in the first core layer 4 provides a high photosensitive response to an optical signal. In a preferred embodiment, the first core layer 4 includes a high concentration of Germanium

dopant, for example 17 %wt, co-doped with Boron, for example 5 %wt. Other dopant ions can be included, or a mixture of dopant ions, for example, tin, cerium, and/or sodium.

The dopant and co-dopants are introduced during the deposition of the first core layer 4. The Germanium dopant induces a high photosensitive response and the Boron co-dopant lowers the refractive index induced by the high level of Germanium in the first core layer 4. The concentrations of the dopant and co-dopant are adjusted to 17% wt and 5% wt to give a difference between the refractive index of the first core layer 4 and the refractive index of the buffer layer 3 of 0.75% which lies in a preferred range of 0.05% to 2.0% .

The first core layer 4 is then consolidated by a suitable method, for example by a second pass of the FHD burner or by consolidating the waveguide 1 in an electrical furnace.

Fig. 1B shows a further stage in the fabrication of the waveguide 1 in which a second core layer 5 is formed on the first core layer 4.

The second core layer 5 is deposited on the first core layer 4 using a suitable method, for example FHD, and is then suitably consolidated, for example, in an electrical furnace.

The second core layer 5 is doped with rare earth dopant ions, for example Er^{+3}, using an aérosol doping technique, and co-doped, for example, with Phosphorus during the deposition of the second core layer 5. The thickness of the second core layer 5 is 4μm, which lies in the range of 0.2μm to 30μm.

Alternative methods can be used to dope the second core layer 5 such as solution doping. Preferably, the dopant and co-dopant are simultaneously introduced in a controlled manner during the deposition of the second core layer 5. The concentrations of the dopant and co-dopant can be controlled so that the second core layer 5 provides the desired signal gain for optical signals propagating through the waveguide and also to ensure that the refractive index of the second core layer 5 is matched to the refractive index of the first core layer 4. In this embodiment, the indices are substantially matched. Alternatively, the first core layer 4 and the second core layer 5 can be subjected to a further process, for example, UV trimming, to effect matching of their refractive indices.

The photosensitive response of the first core layer 4 in combination with the optical signal gain of the second core layer 5 effect the overall level of optical signal amplification provided by the waveguide 1.

A waveguide core 6 is then formed from the first core layer 4 and the second core layer 5 by using a suitable method, for example conventional photolithographic and/or reactive ion etching (RIE) methods. A portion of the second core layer 5 is suitably masked and the unwanted portions of the second core layer 5 and the underlying first core layer 4 are etched away to leave the waveguide core 6. The overall dimensions of the waveguide core 6 formed are $6\mu m$ x $6\mu m$ which is in a preferred range of $0.4\mu m$ x $0.4\mu m$ to $60\ \mu m$ x $60\mu m$.

The co-dopant, here Boron, in the first core layer 4 reduce the refractive index of the waveguide core 6 and enable single mode operation even for large waveguide cores, for example waveguide cores whose dimensions are

in the range of 0.4μm x 0.4μm to 60 μm x 60μm. The co-dopant in the first core layer 4 can also provide other advantages such as enabling higher refractive index changes to occur during later stages of fabrication of a waveguide with multiple core layers.

The first core layer 4 effectively can reduce the optical signal gain provided by the second core layer 5. It is thus advantageous for the first core layer 4 to be as photosensitive as possible in particular as the refractive index modulation no longer occurs over the entire volume of the waveguide core 6.

Fig. 1C shows a further stage in the fabrication of the waveguide. An upper cladding layer 7 is deposited on the waveguide core 6 using an FHD method. The upper cladding layer 7 embeds the waveguide core 6. The upper cladding layer 7 is doped during deposition, for example with Phosphorus and Boron, to adjust its refractive index until the refractive index of the upper cladding layer 7 matches the refractive index of the buffer layer 3. The upper cladding layer 7 is then consolidated, for example in an electrical furnace.

In a second preferred embodiment of the invention, a lower cladding layer is formed on top of the buffer layer 3 before the first core layer 4 is deposited and in which the level of dopant in the upper cladding layer 7 is adjusted until the refractive index of the upper cladding layer 7 matches that of the lower cladding layer. The lower cladding layer can be deposited and consolidated using the same techniques as the upper cladding layer 7.

In an alternative layer structure the first core layer 4 may be deposited on top of the second core layer 5 or

respective first core layers 4 may be provided both below and on top of the second core layer 5. The core layer 5 is then sandwiched between two photo-sensitive first core layers 4 increasing the coupling coefficient of the device.

It is possible also, for certain applications, to dope the photo-sensitive first core layer 4 with a small amount of rare earth ions.

Referring now to Figs. 2A and 2B of the drawings, there is shown a schematic diagram of laser waveguide according to the invention. Figs. 2A and 2B show a cross-section parallel to the longitudinal axis of the laser waveguide core, such that the waveguide core is seen only in profile.

Fig. 2A shows a planar laser waveguide 10 incorporating a Bragg grating 11. The laser waveguide 10 includes a silicon substrate layer 12 and a silica buffer layer 13 comprising a thermally oxidised layer of the substrate 12. The buffer layer 13 is formed on the substrate layer 12.

Fig. 2B is an enlarged view of a section of Fig. 2A. A first core layer 14 is deposited and consolidated on the buffer layer 13 and second core layer 15 is deposited and consolidated on the first core layer 14 using the techniques described above for the deposition and consolidation of first and second core layers 4 and 5 in the waveguide 1. The first core layer 14 can alternatively be formed on an lower cladding layer (not shown) formed on buffer layer 13.

The second core layer 15 is doped with neodymium instead of the erbium used as a dopant in the second

core layer 5. Fig. 2A represents a cross-section through the laser waveguide 10 parallel to the direction of light propagation through the waveguide 10 (i.e., normal to the cross-sectional plane through the waveguide shown in Fig. 1C). The waveguide core 16 is formed from said first core layer 14 and said second core layer 15 using the same technique described above for the formation of the first core layer 4 and the second core layer 15.

An upper cladding layer 17 is then deposited on the second core layer 15 and the grating 11. The upper cladding layer 17 is deposited and consolidated using the same methods as described above for the deposition and consolidation of the upper cladding layer 7 in the fabrication of waveguide 1.

The laser cavity of the laser waveguide 10 is fabricated by writing the Bragg grating 11 into a generally central portion of the first core layer 14 and the second core layer 15. Conventionally, the Bragg grating 11 may be written using a KrF excimer laser operating at 248 nm through a quartz phase mask deposited on top of the upper cladding layer.

An input 18 of the laser waveguide 10 provides an optical signal at a pump wavelength to the laser waveguide 10. An optical interference mirror 19 butt-coupled to the input end 18 of the laser waveguide 10 has a high reflectivity (R_{sig} = 99.9%) around the maxima of the desired output wavelength and has a high transmittance at the pump wavelength (T_{pump} > 95%). The grating 11 forms an output coupler at the output 20 of the laser waveguide 10.

The grating 11 is designed for use at 1050 nm and the reflectivity of the grating 11 formed saturates at 80%. The phase mask used to form the grating 11 has a pitch of 720 nm. In other embodiments, however, it is possible to form gratings 11 which can be used at a wavelength in the range of 500 nm to 2100 nm by using suitable phase masks.

In another embodiment of a laser waveguide, a grating 11 can be provided at both the input 18 and the output 20 of the laser waveguide 10, preferably with both gratings having substantially the same Bragg wavelength thus providing a distributed Bragg reflection laser (DBR).

In yet another embodiment, a distributed feedback laser (DFB) can also be formed by having a grating extending along the length of the gain cavity formed by the core layer 5.

Further, a multicavity laser can be formed by butt-coupling another mirror to the output end of the laser waveguide 10. These external mirrors can be bulk mirror butt-coupled or mirrors directly deposited on the ends of the waveguide. A multiple wavelength laser can be provided by photoimprinting a sampled grating in the waveguide core, with precise control of channel spacing. Additionally, a multiple wavelength laser can be achieved by exposing the same core area to very similar UV patterns, with each exposure determining each one of the emission wavelengths of the superimposed Bragg gratings. An additional grating can be defined to provide gain equalisation for the several wavelengths.

Thus, a multicavity laser can be constructed by using

two mirrors and a grating, one mirror and two gratings, or indeed three gratings.

Still further, in a different application, for example, optical amplifiers, a grating can also be formed on the first core layer 4 to act as a "tap" to flatten optical gain spectra.

While several embodiments of the present invention have been described and illustrated, it will be apparent to those skilled in the art once given this disclosure that various modifications, changes, improvements and variations may be made without departing from the spirit or scope of this invention.

Claims:-

1. An optical waveguide with multiple core layers for transmitting an optical signal, the waveguide including:

a substrate;

a waveguide core formed on said substrate; and

an upper cladding layer embedding said waveguide core;

wherein said waveguide core comprises a first core layer and a second core layer.

2. A waveguide as claimed in any preceding claim, wherein the substrate comprises silicon and/or silica and/or sapphire.

3. A waveguide as claimed in either preceding claim, wherein the substrate includes an intermediate layer.

4. A waveguide as claimed in Claim 3, and wherein the intermediate layer includes a buffer layer formed on the substrate.

5. A waveguide as claimed in Claim 4, wherein said buffer layer comprises a thermally oxidised layer of the substrate.

6. A waveguide as claimed in any one of Claims 4 or 5, wherein the intermediate layer further includes a lower cladding layer formed on said buffer layer.

7. A waveguide as claimed in any one of Claims 4 to 6, wherein the thickness of the buffer layer is in the range 5 μm to 20 μm.

8. A waveguide as claimed in any preceding claim, wherein the second core layer is formed on the first core layer and said first core layer is formed on the substrate.

9. A waveguide as claimed in any one of Claims 1 to 7, wherein the first core layer is formed on the second core layer and said second core layer is formed on the substrate.

10. A waveguide as claimed in Claim 8, wherein a further first core layer is formed on the second core layer such that the first core layer sandwiches the second core layer.

11. An optical waveguide as claimed in any preceding claim, wherein the first core layer includes a dopant to permit the first core layer to exhibit a photosensitive response.

12. A waveguide as claimed in any preceding claim, wherein the first core layer includes silica.

13. A waveguide as claimed in any preceding claim, wherein the first core layer includes a germanium oxide and/or a boron oxide.

14. A waveguide as claimed in of Claims 11 to 13, wherein the first core layer dopant includes dopant ions.

15. A waveguide as claimed in Claim 14, wherein the first core layer dopant ions include tin and/or cerium and/or sodium.

16. An optical waveguide as claimed in any preceding

claim, wherein the second core layer includes a dopant to induce amplification of an optical signal transmitted through said waveguide core.

17. A waveguide as claimed in any preceding claim, wherein the second core layer includes silica.

18. A waveguide as claimed in any preceding claim, wherein the second core layer includes a phosphorus oxide.

19. A waveguide as claimed in any of Claims 16 to 18, wherein the second core layer dopants include dopant ions.

20. A waveguide as claimed in Claim 19, wherein the second core layer dopant includes a mobile dopant.

21. A waveguide as claimed in one of Claims 17 to 20, wherein the second core layer dopants include a rare earth and/or a heavy metal and/or compounds of these elements.

22. A waveguide as claimed in Claim 21, wherein the rare earth is Erbium or Neodymium.

23. A waveguide as claimed in any preceding claim, wherein the refractive indices of the first core layer and the second core layer are substantially equal.

24. A waveguide as claimed in any preceding claim, wherein the refractive index of the waveguide core differs from that of the substrate by at least 0.05%.

25. A waveguide as claimed in any preceding claim, wherein the thickness of the first core layer is in the

range 0.2 μm to 30 μm.

26. A waveguide as claimed in any preceding claim, wherein the thickness of the second core layer is in the range 0.2 μm to 30 μm.

27. A waveguide as claimed in Claim 25, wherein the width of the waveguide core lies in the range 0.4 μm to 60 μm.

28. A waveguide as claimed in any one of Claims 6 to 27, wherein the upper cladding layer and the lower cladding layer comprise the same material.

29. A waveguide as claimed in any preceding claim, wherein the refractive index of the substrate and the refractive index of the upper cladding layer are substantially equal.

30. A method of fabricating a waveguide comprising the steps of:

providing a substrate;

forming a waveguide core on the substrate; and

forming an upper cladding layer to embed the waveguide core, wherein the waveguide core is formed from a first core layer and a second core layer.

31. A method as claimed in Claim 30, wherein the formation of the substrate includes the formation of an intermediate layer formed on said substrate.

32. A method as claimed in Claim 31, wherein the formation of the intermediate layer includes the formation of a buffer layer.

33. A method as claimed in Claim 33, wherein the

buffer layer is formed by thermally oxidising the substrate.

34. A method as claimed in any of Claims 32 to 33, wherein the formation of the intermediate layer further includes the formation of a lower cladding layer formed on said buffer layer.

35. A method as claimed in Claim 34, wherein the formation of the lower cladding layer includes doping said lower cladding layer with a dopant.

36. A method as claimed in Claim 34, wherein the dopant includes dopant ions.

37. A method as claimed in any of Claims 30 to 36, wherein the second core layer is formed on the first core layer and wherein the first core layer is formed on the substrate.

38. A waveguide as claimed in any of Claims 30 to 37, wherein the first core layer is formed on the second core layer and said second core layer is formed on the substrate.

39. A waveguide as claimed in Claim 37, wherein a further first core layer is formed on the second core layer such that the first core layer sandwiches the second core layer.

40. A method as claimed in any of Claims 30 to 39, wherein the steps of forming any one of the substrate, first core layer, the second core layer, and the upper cladding layer comprise the steps of:

depositing each layer; and

at least partially consolidating each layer.

41. A method as claimed in Claim 40, wherein any one of the substrate, the first core layer, the second core layer and the upper cladding layer partially consolidated after deposition is fully consolidated with the full consolidation of any other of the first core layer, the second core layer or the upper cladding layer.

42. A method as claimed in any of Claims 30 to 41, wherein the formation of the first core layer includes the doping of the first core layer with a dopant.

43. A method as claimed in Claim 42, wherein the first core layer dopant permits the first core layer to exhibit a photosensitive response.

44. A method as claimed in any of Claims 30 to 43, wherein the formation of the second core layer includes the doping of the second core layer with a dopant.

45. A method as claimed in any of Claims 30 to 44, wherein the second core layer dopant induces amplification of an optical signal transmitted through said waveguide core.

46. A method as claimed in any of Claims 30 to 45, wherein the formation of the substrate includes the doping of the substrate with a dopant.

47. A method as claimed in any one of Claims 42 to 46, wherein the dopant includes dopant ions.

48. A method as claimed in Claim 47, wherein the substrate dopant includes a mobile dopant.

49. A method as claimed in any of Claims 47 to 48,

wherein said first core layer dopant ions include tin and/or cerium and/or sodium.

50. A method as claimed in any of Claims 47 to 49, wherein said second core layer dopant ions include a rare earth and/or a heavy metal and/or compounds thereof.

51. A method as claimed in Claim 50, wherein said rare earth is Erbium and/or Neodymium.

52. A method as claimed in any of Claims 42 to 51, wherein the concentration of the first core layer dopant is selectively controlled during the formation of the first core layer and the concentration of the second core layer dopant is selectively controlled during the formation of the second core layer so that the refractive index of the first core layer and the refractive index of the second core layer are substantially equal.

53. A method as claimed in Claim 52, wherein the concentrations of the first core layer dopant and second core layer dopant are controlled to give a refractive index for the waveguide core which differs from that of the substrate layer by at least 0.05%.

53. A method as claimed in any of claim 34, wherein said lower cladding layer and said buffer layer are formed substantially in the same step.

54. A method as claimed in any of Claims 40 to 53, wherein at least one of the substrate, the first core layer, the second core layer, and the upper cladding layer is deposited by a Flame Hydrolysis Deposition process and/or Chemical Vapour Deposition process.

55. A method as claimed in Claim 54, wherein the Chemical Vapour Deposition process is a Low Pressure Chemical Vapour Deposition process or a Plasma Enhanced Chemical Vapour Deposition process.

56. A method as claimed in any of Claims 40 to 55, wherein the consolidation is by fusing using a Flame Hydrolysis Deposition burner.

57. A method as claimed in any of Claims 40 to 56, wherein the consolidation is by fusing in a furnace.

58. A method as claimed in either of Claims 57 or 58, wherein the step of fusing the lower cladding layer and the step of fusing the first core layer and/or the second core layer are performed simultaneously.

59. A method as claimed in any of Claims 30 to 58, wherein the waveguide core is formed from the first core layer and the second core layer using a dry etching technique and/or a photolithographic technique and/or a mechanical sawing process.

60. A method as claimed in Claim 59, wherein the dry etching technique comprises a reactive ion etching process and/or a plasma etching process and/or an ion milling process.

61. A method as claimed in any of Claims 30 to 60, wherein the waveguide core formed from the first core layer and the second core layer is square or rectangular in cross-section.

62. A laser waveguide with multiple core layers for transmitting an optical signal, the laser waveguide comprising a waveguide as claimed in any one of claims

1 to 29, the laser waveguide further comprising: at least one grating formed in said waveguide core.

63. A laser waveguide as claimed in Claim 62, wherein the laser waveguide further comprises at least one optical interference mirror.

64. A laser waveguide as claimed in Claim 63, wherein the optical interference mirror is provided at the input of the waveguide.

65. A laser waveguide as claimed in Claim 64, wherein the interference mirror is butt-coupled to or directly deposited at the input of the waveguide.

66. A laser waveguide as claimed in any of Claims 62 to 65, wherein the laser waveguide includes two mirrors and a grating.

67. A laser waveguide as claimed in any of Claims 62 to 65, wherein the laser waveguide includes one mirror and two gratings.

68. A laser waveguide as claimed in Claim 62, wherein the laser waveguide includes three gratings.

69. A laser waveguide as claimed in any of Claims 62 to 68, wherein the grating formed is a Bragg grating.

70. A laser waveguide as claimed in any one of Claims 62 to 69, wherein said grating forms an output coupler for said laser waveguide.

71. A laser waveguide as claimed in any one of Claims 62 to 70 further comprising an optical interference

mirror butt coupled to or directly deposited at the output of the waveguide.

72. A method of fabricating a laser waveguide, comprising forming a waveguide according to a method as claimed in any of claims 30 to 61, the method of fabricating the laser waveguide further including the steps of:

forming at least one grating in said waveguide core.

73. A method as claimed in Claim 72, further including the step of attaching at least one optical interference mirror to the waveguide.

74. A method as claimed in Claim 73, wherein the optical interference mirror is attached to an input of the waveguide.

75. A method as claimed in Claim 72 to 74, wherein the grating is formed using a laser operating at a wavelength in the range of 150 nm to 400 nm through a phase mask deposited on top of said upper cladding layer of the waveguide.

76. A method as claimed in Claim 75, wherein said mask is a quartz mask.

77. A method as claimed in Claim 72 to 74, wherein the grating is formed using a using an interference side writing technique.

78. A method as claimed in any one of Claims 72 to 74, wherein the grating is formed using a direct writing technique.

79. A method as claimed in any one of Claims 72 to 78, wherein the grating formed is a Bragg grating.

80. A method as claimed in any one of Claims 73 to 79, wherein the optical interference mirror is butt-coupled to or directly deposited at the input of the waveguide.

81. A method as claimed in any one of Claims 72 to 79, further comprising the step of attaching a second optical interference mirror to the output of the waveguide.

82. A waveguide substantially as described herein and with reference to Figs. 1A to 1C of the accompanying drawings.

83. A laser waveguide substantially as described herein and with reference to Figs. 2A and 2B of the accompanying drawings.

84. A method of fabricating a waveguide with multiple core layers substantially as described herein and with reference to Figs. 1A to 1C of the accompanying drawings.

85. A method of fabricating a laser waveguide with multiple core layers substantially as described herein and with reference to Figs. 2A and 2B of the accompanying drawings.

ABSTRACT OF THE DISCLOSURE

An optical waveguide with multiple core layers for transmitting an optical signal comprises a substrate; an intermediate layer formed on said substrate; a waveguide core formed on said intermediate layer; and an upper cladding layer embedding said waveguide core. The waveguide core comprises a first core layer formed on said intermediate layer and a second core layer formed on said first core layer. The first core layer has photosensitive properties and the second core layer has optical gain properties.

(Figs. 2A and 2B)



FIG. 1A



FIG. 1B



FIG. 1C



FIG. 2A



FIG. 2B

323